

MonniRep MC

Flowable, Non Shrink Micro-Concrete

Product Description

MonniRep MC is a single component, cement based flowable non-shrink micro-concrete. It is composed of Portland cement, graded aggregates and special additives. It is formulated to achieve a high flowability mix with minimal water content which ensures early strength gain and long durability

Uses

MonniRep MC is designed to repair structural damaged concrete. It can be used in small, as well as, large repairing areas. It is ideal to be used in the following cases:

- ▶ Replacing sections of concrete beams.
- ▶ Structural repairs for columns...
- ▶ Repair and fill deep honeycombed concrete
- ▶ Provide hard wearing repairs to concrete flooring

Can be applied in structural membrane where steel reinforcement is congested or access to this area is

Advantages

- ▶ Low alkaline and chloride free product.
- ▶ Economical product for mass concrete repairs
- ▶ Excellent adhesion to concrete substrates
- ▶ Non-shrink, with early strength characteristics
- ▶ Can be poured manually or by pump
- ▶ One component product which makes it easy to mix and apply at site
- ▶ Hardened product exhibits high strength with low permeability.
- ▶ Free flow mix which minimize the risk of honey-comb and eliminate the need for vibration process without any risk of segregation.

Usage Instructions

Concrete preparation

The surface of the concrete to be repaired should be sound, clean and uncontaminated. The boundary of the repair area should be cut using a concrete saw to provide a neat edge to the repair with no feather edging and to provide a square edge. Repairs using MonniRep MC should be generally at least 50 mm as a minimum depth with a maximum of 500 mm in single coat.

Oil and grease deposits should be removed by stiff brushing, detergent scrubbing with a heavy-duty cleaner/degreaser or steam cleaning.

Prepare the formwork to be rigid and tight to prevent loss of material. The formwork should include drainage outlets for presoaking.

Steel Preparation

Any corroded steel in the repair area must be fully exposed. All exposed reinforcement shall be cleaned of corrosion products by wet grit blasting or other approved means to achieve a clean and bright finish.

In case that reinforcing bars, section is reduced due to oxidization, integrate them with additional bar reinforcement.

Priming

The cleaned steel should be coated within 3 hours. Apply one coat of MonniRep CS, a corrosion proof cementitious based primer or MonniZinc, a two component Zinc rich Epoxy Primer, continuously with brush onto the cleaned bar reinforcement ensuring that the whole steel surface area is completely covered. Allow to dry before continuing.

MonniRep MC must be applied before the bonding agent dries while it's still tacky to achieve a better bond between the fresh and cured section.

Mixing

To prepare the mortar, it is recommended to have a forced-mixer of spiral paddle in a slow speed (300/400 rpm) heavy duty drill. It is essential that machine mixing capacity and labor availability is adequate to enable the placing operation to be carried out continuously.

Add 3.3 – 3.5 liters of water in the mixing drum then add the full bag of MonniRep MC and mix for at least 4 – 5 minutes till obtaining a fluid, uniform lump free consistency mix.

Do not part mix the bags, nor use additional water than specified. Note that powder must always be added to water.

To obtain the full benefit of the fluidity provided, apply MonniRep MC immediately after mixing.

Application

Cast the mortar into the formwork, allowing air to escape. It's advisable to spray the formwork by water prior to placing the mortar to avoid water absorption from the mix. Use trowel or sponge for the finishing touch.

Curing

The repaired area shall be cured in accordance with good concrete curing practice and protected from drying winds, sun or excessive heat. Curing shall be done with non-degradable curing compound MonniCure AR. Alternatively; a wet hessian cloth covered with polyethylene sheet can also be employed. Curing should begin as soon as final finish is achieved.

Cleaning

MonniRep MC should be removed from tools and equipment and mixers with clean water immediately after use. Cured material should be removed mechanically.

Technical Data

Category	Typical Values
Appearance	Grey powder
Wet density	2.3 kg/L at 25°C
VOC	2.0 g/L
Granulometry	10mm
Compressive strength at 7 days at 28 days (ASTM C579)	46 N / mm ² 65 N / mm ²
Flexural strength at 7 (ASTM C580)	7.5 N / mm ²
Tensile strength at 28 days (BS 6319 – 7)	4.0 N / mm ²
Slant Shear Strength (ASTM C 882)	7.6 N / mm ²
Drying Shrinkage at 28 days (ASTM C157 93)	< 500 microstrain
Coefficient of thermal expansion (BS 6431 15)	1 x 10 ⁻⁶ μm
Chloride Ion Penetration (ASTM C1202)	Low
Water Absorption (BS 1881 Pt 122)	< 1.9%
Water Penetration (BS EN 12391 Pt 8)	NIL
Setting time Initial Final	2.5 hours 4.5 hours
Workability	>30 minutes @25 °C

All values are subject to 5-10% tolerance

Yield

12.5 liters / 25 kg bag with 3.5 liters water addition

Packaging

MonniRep MC is packed in 25 Kg bags

Shelf Life & Storage

Keep the product in dry covered place into original well closed packaging. In these conditions, the product will have a shelf life of 12 months from date of production.

Health & Safety

MonniRep MC can be harmful to skin as it contains cement powders which may releases alkalis when mixed with water.

During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment if necessary.

In case of contact with skin, rinse with water and again wash thoroughly with soap and water. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly.

If ingested, obtain medical attention immediately. Do not induce vomiting.

Legal disclaimer

Monneli endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Monneli has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

VER.1.2019