

# MonniProof BE

Cold applied bitumen emulsion

## Product Description

MonniProof BE is a cold applied water based bitumen with special additives. It is a blend of selected bitumen emulsified with water to give an easily applied protective coating. Once cured, MonniProof BE forms a seamless film with great adhesion to the substrate.

## Uses

- ▶ General waterproofing and protective coating for concrete, screeds, masonry, metal surfaces, pipes and many other surfaces
- ▶ As vapor/salt barrier and damp proofing behind granite, marble, curtain walls, etc.
- ▶ Sealer for concrete before applying the top finishing coats.
- ▶ As a curing membrane for concrete below ground
- ▶ Protective coating to concrete slabs above false ceiling, bulk heads etc.

## Advantages

- ▶ Economical
- ▶ Easily to apply
- ▶ Contains no solvents
- ▶ Excellent Adhesion
- ▶ Can be applied over damp surface
- ▶ Compatible with all bituminous products
- ▶ Cured film resists water, diluted acids, alkalis and chloride
- ▶ Anti-fungal and anti-bacterial

## Instructions for Use

### Surface Preparation

The surface of the concrete shall be sound, clean and uncontaminated.

This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base.

Moss and lichen must be removed physically followed by treatment with fungicidal wash. After treatment, it must be washed down thoroughly with clean water and allow to dry.

### Priming

Hot, very dry or porous surfaces should be primed before applying MonniProof BE.

### Mixing

MonniProof BE should be stirred before use until a uniform color and consistency is achieved. Product is ready for use.

### Application

For waterproofing underground structures, the bituminous emulsion shall be applied by brush or squeegee at a maximum rate of 200 microns per coat. The two coats must be applied at right angles to one another with a minimum of 6 hour intervals between each application at 25°C. Each coat must be completely dry before the next coat is applied.

### Cleaning

Clean the tools immediately after use with clean water. During work, it is recommended to place the tools in water while not in use. Cured materials can be removed mechanically.

## Technical Data

Category	Typical Values
Appearance	dark brown dries to seamless black coating
Density at 25°C	1.01 kg/L
VOC	10.0 kg/L
Solid Content	Up to 35%
Flash point	non-flammable
Elongation (ASTM D412)	600%
Tensile Adhesion Strength	>2.0 N/mm <sup>2</sup>
Service temperature	-5°C to +80°C

All values are subject to 5-10% tolerance

## Standards Compliance

- ▶ ASTM D 2939 & D 1227
- ▶ ASTM C 309-93

## Consumption

2 – 4 m<sup>2</sup> / Liter depending on porosity of substrate.

## Packaging

MonniProof BE is packed in 20 Liter and 200 Liter Drums.

## Shelf Life & Storage

Should be stored under cover away from extreme heat, direct sunlight or frost. Shelf life is 12 months if stored tightly sealed containers under good storage conditions.

## Health & Safety

MonniProof BE is non-flammable, non-hazardous product. However, proper measures should be taken during work to avoid contact with eyes or skin. In the event of contact with eyes, irrigate immediately with clean water and seek medical care.

## Legal disclaimer

Monneli endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Monneli has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

VER.1.2019