

MonniProof RBL

Rubberized Bitumen Emulsion

Product Description

MonniProof RBL is a cold applied rubberized bitumen emulsion in dark brown color that, when dries, it forms tough black seamless and flexible coating.

Uses

- ▶ Provides a sandwich membrane between screed flooring
- ▶ A waterproofing coat for concrete foundations, bricks, retaining walls, etc.
- ▶ It can be used to waterproof walls and floors in wet areas
- ▶ For maintenance of many types of roofs including built up felt, aluminum, concrete, lightweight screed, timber, slate, asbestos, bitumen sheets, etc.
- ▶ As a vapour/salt barrier for exterior walls to building facades behind granite, marble, stone, cladding, curtain walls, etc.
- ▶ Can be used as adhesive for insulation boards and expanded polystyrene

Advantages

- ▶ Economical
- ▶ Water based with excellent adhesion
- ▶ Nonflammable
- ▶ Easily applied by brush or squeegee.
- ▶ Excellent resistant to alkalis, mild acids, chlorine
- ▶ Compatible with all bituminous products
- ▶ Resistant to chlorides and sulfates

Instructions for Use

Surface Preparation

The surface of the concrete shall be sound, clean and uncontaminated.

This preparation shall be such as to leave a sound exposed concrete surface free from dust, loose particles and any deleterious matter. If the concrete surface is defective or has laitance, it must be cut back to a sound base.

Moss and lichen must be removed physically followed by treatment with fungicidal wash. After treatment, it must be washed down thoroughly with clean water and allow to dry.

Priming

Hot, very dry or porous surfaces should be primed before applying MonniProof RBL.

Mixing

MonniProof RBL should be stirred before use until a uniform color and consistency is achieved. Product is ready for use.

Application

For waterproofing underground structures, the bituminous emulsion shall be applied by brush or squeegee at a maximum rate of 200 microns per coat. The two coats must be applied at right angles to one another with a minimum of 6 hour intervals between each application at 25°C. Each coat must be completely dry before the next coat is applied.

Cleaning

MonniProof RBL products should be removed from tools, equipment and mixers with clean water prior to the initial set. Cured material can only be removed mechanically.

Recommendation

Do not apply subsequent applications if the membrane is punctured or damaged

Technical Data

Category	Typical Values
Appearance	dark brown dries to seamless black coating
Density at 25°C	1.0 kg/L
VOC	30.0 g/L
Solid Content	>50%
Rubber Content	≥ 10%
Water resistance	Good
Chloride resistance	Excellent
Flash point	Non-flammable
Application temperature	+5°C to +35°C
Service temperature	-5°C to +80°C

All values are subject to 5-10% tolerance

Standards Compliance

- ▶ ASTM D 1187, D 2939
- ▶ BS 8102
- ▶ ASTM D1227, Type III Class 1 & 2

Consumption

2 – 4 m² / liter

Packaging

MonniProof RBL is packed in 200 Liter Drums.

Shelf Life & Storage

Should be stored under cover away from extreme heat or direct sunlight or frost. Shelf life is 12 months in tightly sealed containers if stored properly.

Health & Safety

MonniProof RBL is non-flammable, non-hazardous product. However, proper measures should be taken during work to avoid contact with eyes or skin. In the event of contact with eyes, irrigate immediately with clean water and seek medical care.

Legal disclaimer

Monneli endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Monneli has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

VER.1.2019