

Monneli EPS Mortar

Adhesive for EPS Panels

Product Description

Monneli EPS Mortar is a powder adhesive composed of hydraulic binders, bonding agent, selected aggregates synthetic resins and special additives. It is supplied as a dry powder in pre-weighed bags ready to use on site, which requires only addition of clean water to produce easily workable mortar. Monneli EPS Mortar is ideal for fixing EPS Panels.

Uses

- ▶ For laying internal or external EPS Panels.
- ▶ For repairing EPS Structures.

Advantages

- ▶ Factory controlled pre-blend ensures consistent high quality.
- ▶ Requires only addition of water on-site at the time of usage.
- ▶ High adhesion.
- ▶ Good mechanical strength.
- ▶ Excellent workability.
- ▶ Suitable for internal & external applications.

Usage Instructions

Substrate Preparation

The EPS panel surface should be sound, clean, free from loose material, grease, laitance, dirt curing compound, etc.

Prior to Monneli EPS Mortar application, wet the entire surface with clean potable water. The surface should look damp at the time of Monneli EPS Mortar application.

Mixing

Add to the mixing container 3.8-4 litres of clean water for 25 Kg bag of Monneli EPS Mortar. Add the powder to the water and mix with a mechanical plaster mixer

or low speed electric drill fitted with a suitable paddle for 3-4 minutes, until a uniform, lump-free consistency is achieved.

Manual mixing is allowed for small batch quantities by mixing for approx. 1-2 min, or when homogenous mix is achieved.

Application

Neutralize the suction of the block surface with water before applying mortar. Any excess water should be removed.

Ensure that the first layer of panels is fixed properly with perfect alignment.

The Monneli EPS Mortar is spread with trowel on the surface and joints where the panels are to be mounted.

Monneli EPS Mortar should be applied in a thin layer to enable the continuity of thermo-insulation of the panels. Leave a space of about 2 cm between the top of panel wall and the bottom of slab or beam. This cavity should be filled with compressible material.

If the panels are laid directly on a floor with possible humidity rising, it is recommended to apply a proper damp course system first.

Cleaning

All tools should be cleaned immediately after finishing by water. Hardened materials can be cleaned mechanically.

Technical Data

Category	Typical Values
Appearance	White & Grey Powder
Aggregate Size	1.0 mm (max)
Application Thickness	3-10 mm
Wet Density	1.70 Kg/L (approx.)
Dry Density	1.30 Kg/L (approx.)
Pot Time	1 hr @ 25°C
Compressive Strength (BS EN 1015-11)	≥ 10 N/mm ² @ 28 days
Flexural Strength (BS EN 1015-11)	≥ 1.20 N/mm ² @ 28 days
Adhesive Strength	≥ 0.5N/mm ² @ 28 days

All values are subject to 5-10% tolerance

Standards Compliance

- ▶ BS EN 998-2

Consumption

Monneli EPS Mortar usage yields 1.3-1.5 Kg per square meter for 1 mm thickness.

Packaging

Monneli EPS Mortar is supplied in 25 & 50 Kg bag sizes.

Shelf Life & Storage

Original sealed bags of Monneli EPS Mortar has a shelf life of 12 months provided it is stored clear of ground in a dry shaded place below 25 °C.

Recommendations

- ▶ After application, avoid rapid evaporation of water that may cause the small superficial fissures appearance due to plastic shrinkage.
- ▶ Damp the surface for the initial 48 hours by spraying water and covering it with impermeable sheets. Subsequent plastering may commence after 1 day during summer, and preferably after 2-3 days during winter season.
- ▶ The product should not be exposed to moving water during application.
- ▶ Do not apply the product at temperature less than +5 °C. During summer season the working area must be covered to prevent ill-effects from direct sun.

Health & Safety

Monneli EPS Mortar is highly alkaline therefore avoid direct contact with eyes or skin. It is recommended to use protective gloves and goggles during application. Any skin contact should be wash with soap & water. In case of eyes irritation, immediately wash with copious amount of clean cold water. Seek medical advise.

Monneli EPS Mortar is non-flammable.

For further information, please refer to material safety data sheet.

Legal disclaimer

Monneli endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Monneli has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.