

# MonniSeal°1200 WMR-UV

1.2 mm thick reinforced PVC Membrane for exposed roofing system

## Product Description

MonniSeal 1200 WMR-UV is a homogeneous PVC (polyvinylchloride) sheet waterproofing membrane Ultraviolet Resistant and reinforced with polyester mesh.

## Properties

Appearance:	Reinforced PVC rolled sheet membrane
Membrane thickness:	1.20mm
Colour:	Grey

## Uses

Waterproofing of exposed Roofs and podiums

## Advantages

- High tensile strength and elongation
- Hot air weldable
- Flexible throughout life span
- Resistant to ageing
- Long durability
- High dimensional stability
- Anti-Root membrane
- Can be installed on wet and dry substrates
- Designed to be used in hot climates
- Reaction to Fire - Class B
- Covered Application

## Standards

Tested according to testing requirements of ASTM D4434 and DIN 16735.

## Technical Data

Test Performed	Standard and Requirements	Results
Membrane Thickness	ASTM D 4434	1.2 mm
Mass	DIN16735	1.56 kg/m <sup>2</sup>
Tensile strength	DIN 16735 Min 10.40 N/mm <sup>2</sup>	≥11.0 N/mm <sup>2</sup>
Elongation at break	DIN 16735 Min 150%	>300%
Thermal Stability	DIN 16735 Less than 1% (6 hrs - 90°C)	<0.3%
Tear Strength	Min 80 N	> 5N
Seam Strength	ASTM D 4434	>82%
Tear Resistance	ASTM D 4434	>95 N
Puncture Resistance	DIN 16735 Drop hammer 500 grams, from 300mm no leak	Passed
Water Vapour diffusion Resistance	DIN16735 Less than 30,000	<23,000 μ
Cold Bend	DIN 16735 No cracks at -20°C	No cracks at -30°C
Resistance to Algae & Rot		High resistance

### Complementary products:

PVC Coated Aluminium sheet for termination Geotextile membrane  
 Protection layer  
 PU Sealant  
 Aluminium flashing  
 Steel washers

### Instructions of use:

#### Substrate Preparation

The surface of the sloping concrete shall be sound, clean, dry or wet, and uncontaminated. This preparation shall be as such as to leave a sound exposed concrete surface free from dust, laitance and any delirious matter.

#### Application:

##### LOOSELY LAID PVC SHEET INSTALLATION

Install loosely laid PVC sheets over entire roof area so the light colour is at the visible side towards the substrate.

**A. Horizontal Installation:**

1. Install the separation layer over the entire horizontal area before the PVC membrane (if needed) in full accordance with Monneli's method statement
2. Accurately align sheets and maintain uniform side and end laps of minimum dimensions required. Stagger end laps.
3. Install the Geotextile membrane as a separation layer above the PVC membrane followed by a minimum of 50mm extruded polystyrene thermal insulation
4. As much as practically possible the joints will not be against the direction of flow.

**Upstands:**

1. Apply the 1200 WM-FB membrane directly on the concrete up-stand with **Neofil S10** contact adhesive
2. Secure top termination of waterproofing with continuous, Aluminum flashing strip, and MonniSeal PU25, a Polyurethane sealant from Monneli.

**Seam Installation:** Hot air welding and end laps of overlapping sheets according to manufacturer's method statement to ensure a watertight seam installation. Inspect outside edge of seams with pointed metal probe and ensure completed laps lay flat through one of the following methods:

1. Method 1: All seams of installed waterproofing can be subject to pneumatic test at test pressure of 2.00 bars.
2. Method 2: Testing the welded joint using a vacuum test machine

- D. Any hole, resulting from construction activities, noted in installed membrane shall be repaired in accordance with manufacturer's method statement.

**CORNER JOINT INSTALLATION**

- A. Install corner details in accordance to waterproofing manufacturer's written instructions.
1. Use same welding system as specified for membrane.

**Ambient Air Temperature**

+5°C - +60°C

**Packaging**

Roll size: 2.10 m (roll width) x 20m (roll length)

**Storage**

Rolls shall be stored in their original package, in horizontal position and under cool and dry conditions protected from direct sunlight and rain. MonniSeal PVC membrane does not expire and has a very long life expectancy.

## Limitations

- Do not directly apply the PVC membrane permanently on bitumen and plastics other than PVC, a separation layer of geotextile is required.
- The PVC membrane can be exposed to temporary UV light for a period of 6 months
- MonniSeal 1200 WM-FB can be exposed temporary to ground water or polluted water with temperature up to 50°C for 3 months.

## Health and Safety

- Local safety regulations must be observed. Information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet.

## Legal disclaimer

Monneli endeavors to ensure that any advice, recommendations, information it may give, is accurate and correct. It cannot accept any liability either directly or indirectly arising from the use of its products, because it has no direct or continuous control over where or how its products are applied, whether or not in accordance with any advice, specification, recommendation or information given by us. Monneli has the right to change any of the specifications mentioned in the Technical data sheets upon its discretion without prior notification. Hard copies of TDSs are printed once or twice a year, while our technical data sheets are continuously being updated as per R&D improvements and new 3rd party testing; kindly refer to our website for the latest updated TDSs.

VER.1.2019